



(19)

(11) Publication number: **1**

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **09039134**(51) Intl. Cl.: **C23C 16/36 B23P 15/28 C2**
29/02(22) Application date: **24.02.97**

(30) Priority:	(71) Applicant: SUMITOMO ELECTRI
(43) Date of application publication: 08.09.98	(72) Inventor: TSUDA KEIICHI IKEGAYA AKIHIKO
(84) Designated contracting states:	(74) Representative:

(54) WC BASE CEMENTED CARBIDE AND ITS PRODUCTION

(57) Abstract:

PROBLEM TO BE SOLVED: To produce a WC base cemented carbide most suitable as a substitute for a coating tool as a tool material for cutting and to provide a method therefor.

SOLUTION: In a sintered alloy composed of hard phases of carbide, nitride and carbonitride contg. W and Ti as essential component, at least one kind among Mo, V, Nb, Ta, Zr and Hf and N(nitrogen) and C(carbon) by 75 to 95wt.%, and the balance a binding phase essentially consisting of iron group metal with inevitable impurities, the content of W in the sintered alloy is regulated to 60 to 90wt.% expressed in terms of WC, the content of Ti is regulated to 3 to 30wt.% expressed in terms of TiN or TiN and TiC, the total content of Mo, V, Nb, Ta, Zr and Hf is

regulated to 0.5 to 10wt.% expressed in terms of Mo₂C, VC, NbC, TaC, ZrC and HfC, a carbonitride layer having 5 to 15 μ m thickness is present on the surface, the layer is composed of mutual solid solution consisting of all of the metallic components in the hard phases contained in the alloy, N and C, and the surface roughness regulated to $\geq 1.5\mu$ m by Ra.

COPYRIGHT: (C)1998,JPO

The Delphion Integrated View

Get Now: [More choices...](#)Tools: Add to Work File: [Create new Wor](#)View: [INPADOC](#) | Jump to: [Top](#)  Go to: [Derwent...](#) [Em](#)Title: **JP10237650A2: WC BASE CEMENTED CARBIDE AND ITS PRODUC**Country: **JP Japan**Kind: **A**Inventor: **TSUDA KEIICHI;
IKEGAYA AKIHIKO;**Assignee: **SUMITOMO ELECTRIC IND LTD**
[News, Profiles, Stocks and More about this company](#)Published / Filed **1998-09-08 / 1997-02-24**Application **JP1997000039134**

Number:


IPC Code: **C23C 16/36; B23P 15/28; C22C 1/05; C22C 29/02; B23B 27/14;**Priority Number: **1997-02- JP1997000039134**

Abstract:

PROBLEM TO BE SOLVED: To produce a WC base cemented carbide most suitable as a substitute for a coating tool as a tool material for cutting and to provide a method therefor.

SOLUTION: In a sintered alloy composed of hard phases of carbide, nitride and carbonitride contg. W and Ti as essential component, at least one kind among Mo, V, Nb, Ta, Zr and Hf and N(nitrogen) and C(carbon) by 75 to 95wt.%, and the balance a binding phase essentially consisting of iron group metal with inevitable impurities, the content of W in the sintered alloy is regulated to 60 to 90wt.% expressed in terms of WC, the content of Ti is regulated to 3 to 30wt.% expressed in terms of TiN or TiN and TiC, the total content of Mo, V, Nb, Ta, Zr and Hf is regulated to 0.5 to 10wt.% expressed in terms of Mo₂C, VC, NbC, TaC, ZrC and HfC, a carbonitride layer having 5 to 15μm thickness is present on the surface, the layer is composed of mutual solid solution consisting of all of the metallic components in the hard phases contained in the alloy, N and C, and the surface roughness regulated to ?1.5μm by Ra.

COPYRIGHT: (C)1998,JPO

Family: **None**Other Abstract **DERABS C98-537950 DERC98-537950**
Info:

Nominate

[this for the Gallery...](#)

© 1997-2003 Thomson Delphion

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Conta](#)